

VIKING™ TarRestore

PRODUCT DESCRIPTION

Designed for compatibility and rejuvenation of coal tar pitch roofing systems, Viking Tar Restore combines a select blend of refined coal tar pitch, aromatic solvents, non-asbestos fibers and fillers, and wet adhesion surfactants that extend the life of coal tar pitch roofing systems. This cold-applied resaturant is highly resistant to chemical and ultraviolet attack, curing to a tough, durable protective barrier. Viking Tar Restore's unique self-healing properties and ponding water resistance make it ideal for no to low slope roofs.

USES

- A cold applied coating/resaturant for use with coal tar pitch BUR roofing.
- Waterproofing and dampproofing of concrete and masonry surfaces.

SURFACE PREPARATION

All surfaces must be clean, free of heavy dirt, dust, debris, oils, loose gravel, un-adhered coatings, scaling rust, deteriorated membranes, and other contaminants that may result in a surface that is not sound. Surface must be free of frost, snow and ice. Aggregate must be spud away to provide a proper work surface. Fasteners must be repaired and/or replaced as needed.

PRECAUTIONS

- DO NOT use with/on 100% rubber or plastic substrates.
- DO NOT use on or with products containing asphalt.
- DO NOT use where this product may come in contact with potable water.
- DO NOT HEAT.
- DO NOT THIN.
- EXTERIOR USE ONLY.

APPLICATION

Ready to apply. Cold apply Viking Tar Restore with a squeegee or roller. In cold weather, store at 70-80°F (21.1-26.7°C) for 24 hours prior to application or use an OSHA-approved pail/drum heater.

- If used as a coating over metal or composition roofs, apply Viking Tar Restore to the prepared surface at a rate of 2-4 gallons (7.6-15.1 liters) per square.
- Apply to the prepared gravel surfaced roof at a rate of 4-8 gallons (15.1-30.3 liters) per square.
- Re-embed gravel.

PACKAGING

5-gallon pails (52 lbs.) and 55-gallon drums (572 lbs.)

SPECIFICATION COMPLIANCES

Federal Specification SS-C-540B (except, non-asbestos)

Technical Data	Viking Tar Restore
Weight (lbs./gal.) D6511	8.8-9.2
Total Solids % by wt D6511	87-92
% by vol	83-87
Viscosity, grams Stormer to 200 revolutions	500-1500
Flash Point PMCC	105°F (40.5°C)
Color, Uncured & Cured Visual	Black
Drying Time, Touch 70°F (21.1°C)/50% R.H.	8 hours
Shelf Life 70°F (21.1°C)/50% R.H.	1 year
VOC EPA Method 24A	200 g/L max