

Storm Breaker™ Rust Inhibitive Primer

TECHNICAL PRODUCT INFORMATION



Storm Breaker Rust-Inhibitive Primer is a high quality, water based rust-inhibiting primer, specially designed for application over metal roof surfaces to prevent rust growth and prime the surface for a top coating application. Rust-Inhibitive Primer can be applied by sprayer, brush, or roller. Low VOC's and a water based formulation mean easy clean up.

FEATURES & BENEFITS

Storm Breaker Rust-Inhibitive Primer offers many benefits:

- Water based primer means easy clean up
- Single component, ready to use
- Provides excellent adhesion for Storm Breaker coatings over existing metal roofs
- Prevents discoloration of the top coating due to existing rust

PACKAGING

Storm Breaker Rust-Inhibitive Primer is red in color and is available packaged in 5-gallon pails (36 pails / pallet).

STORAGE & HANDLING

Keep containers tightly closed and in a cool, dry location. When stored unopened and in temperatures between 40°F (4.4°C) and 70°F (21.1°C), Storm Breaker Rust-Inhibitive Primer has a recommended shelf life of 12 months from the date of manufacture. Always protect from freezing during shipment and while in storage.

APPLICATION

The surface to be coated must be clean, dry, and sound, as well as free of dirt, moisture, oils, algae, or other contaminants that may interfere with good adhesion. Carefully remove any loose material from the surface with a wire brush or scraper. Grease and oil should also be removed with environmentally safe solvents or an appropriate cleaner. In most cases, a high pressure water blast will be sufficient to prepare the surface. With all coatings, proper preparation is key to yielding the optimal results. BITEC always recommends adhesion testing prior to starting any roof coating jobs.

Product application should be suspended immediately and our technical service personnel contacted if the results being obtained are less than desirable.

Storm Breaker Rust-Inhibitive Primer requires evaporation to cure as it is a water based material. It should not be applied

when the ambient temperature is below 50°F (10°C) or if the temperature will fall to less than 32°F (0°C) within 24 hours after application. BITEC does not recommend applying Rust-Inhibitive Primer if rain or dew is likely to occur before the product dries. If high humidity is present, application should be avoided in the late afternoon as overnight dew formation on uncured surfaces can cause the coating to wash off. On marginal days, multiple thin coat applications can help to ensure that the coating can dry before rain occurs or overnight freezing temperatures are a risk. Cure time can be slowed by cooler temperatures and/or high humidity.

While it can also be applied with a brush or roller, Storm Breaker Rust-Inhibitive Primer is intended to be spray applied. The application rate should be 1 gallon / 200 ft². The existing roof surface should be clean and dry prior to application. Never leave this applied product exposed to the elements for more than 48 hours. If left exposed, excessive weathering and dirt pick up can occur, compromising adhesive performance.

For specific information on spray pump, hose, and spray gun requirements, please contact BITEC Technical Services.

PRECAUTIONS

As with all chemicals, avoid getting this product on you or in you. Wash thoroughly after handling this product. Do not eat, drink, smoke, or apply cosmetics while handling this product. Avoid breathing vapors / mists generated by this product. Use in a well-ventilated location. Remove contaminated clothing immediately.

Safety first! Read all label information, SDS, and precautions before using. For safety information on our products, please visit www.bitec.com.

Storm Breaker™ Rust Inhibitive Primer

TECHNICAL PRODUCT INFORMATION



Technical Schedule	
Appearance	Red
Total Solids (Volume)	41% +/- 2%
Weight	10 lbs / gal +/- 0.2
VOC	<65 g / L
Clean Up	Water
Shelf Life	12 months
Viscosity	800 +/- 200cP

All information is given in good faith but normal tolerances of manufacture and testing will apply. BITEC reserves the right to improve and change its products at any time without prior notice or advice. The use of BITEC products is determined by local conditions and individual requirements of each contract. In consideration of the many factors involved, BITEC cannot be held responsible for the application of its products and for conditions beyond its control. All claims filed against BITEC warranties will be subject to the provisions set forth at the date of the warranty issuance, and any addendum thereto. Under no circumstances will BITEC be held liable for any damage, whether personal injury or property damage, which occur during or after the application of any BITEC products.

Copyright BITEC, Inc.
Revision Date 01/2025



BITEC, Inc.
PO Box 497
#2 Industrial Park Dr
Morrilton, AR 72110
Phone: (800) 535-8597
Fax: (501) 354-3019
www.bitec.com

BITEC®

WHEN QUALITY MATTERS™