

Storm Breaker SEBS Rubberized Skylight Coating is a clear, elastomeric, solvent based coating designed to waterproof fiberglass skylight panels and other translucent skylights. It can be applied by spray, brush, or roller. SEBS Rubberized Skylight Coating can help extend the life of existing skylights and allow them to stay in use.

FEATURES & BENEFITS

Storm Breaker SEBS Rubberized Skylight Coating offers many benefits:

- Clear coating to protect existing skylights and allow them to continue functioning as skylights
- Can be sprayed, brushed, or roller for ease of application
- Also makes an ideal sealant for decorative metal surfaces

PACKAGING

Storm Breaker SEBS Rubberized Skylight Coating is available as a clear product, packaged in 5-gallon pails (36 pails / pallet).

STORAGE & HANDLING

Store locked up and in a well-ventilated location. Keep containers tightly closed. When stored unopened and in temperatures between 45°F (7.2°C) and 95°F (35°C), SEBS Rubberized Skylight Coating has a recommended shelf life of 24 months from the date of manufacture.

APPLICATION

The surface to be coated must be clean, dry, and sound, as well as free of dirt, moisture, oils, algae, or other contaminants that may interfere with good adhesion. Carefully remove any loose material from the surface with a wire brush or scraper. Grease and oil should also be removed with environmentally safe solvents or an appropriate cleaner. In most cases, a high pressure water blast will be sufficient to prepare the surface. With all coatings, proper preparation is key to yielding the optimal results. BITEC always recommends adhesion testing prior to starting any roof coating jobs.

Product application should be suspended immediately and our technical service personnel contacted if the results being obtained are less than desirable.

Storm Breaker SEBS Rubberized Skylight Coating is best applied when ambient temperatures are 50°F (10°C) and rising. Substrate temperatures must not exceed 130°F (54.4°C). For optimal spray application, the roof coating

should be at a minimum temperature of 60°F (15.6°C). At lower temperatures, brush or medium nap roller application is recommended. Use caution if exceeding 24 wet mils or using dark colors as the likelihood of blistering increases.

PRECAUTIONS

Always follow good roofing practices when deciding if the current weather conditions are conducive to a good installation. Avoid breathing vapors / mists generated by this product and always use in a well ventilated location. Keep away from heat, hot surfaces, sparks, open flames, and other sources of ignition.

Safety first! Read all label information, SDS, and precautions before using. For safety information on our products, please visit www.bitec.com.

Technical Schedule	
Viscosity (78°F / 25.6°C)	1,200 cps
Solids (% by weight)	37%
Weight	7.5 lbs / gal
Elongation	1000%
Tensile Strength	1800 psi
VOC	<550 g / L
Flash Point	103°F (39.4°C)
Shelf Life	24 months
Appearance	Clear

All information is given in good faith but normal tolerances of manufacture and testing will apply. BITEC reserves the right to improve and change its products at any time without prior notice or advice. The use of BITEC products is determined by local conditions and individual requirements of each contract. In consideration of the many factors involved, BITEC cannot be held responsible for the application of its products and for conditions beyond its control. All claims filed against BITEC warranties will be subject to the provisions set forth at the date of the warranty issuance, and any addendum thereto. Under no circumstances will BITEC be held liable for any damage, whether personal injury or property damage, which occur during or after the application of any BITEC products.

BITEC, Inc.
PO Box 497
#2 Industrial Park Dr
Morrilton, AR 72110
Phone: (800) 535-8597
Fax: (501) 354-3019
www.bitec.com

